



TECHNICAL DATA SHEET

TAFTLOCK 22

Anaerobic Thread Locker

Updated: Sept 2018

PRODUCT DESCRIPTION

TAFTLOCK 22 is a low strength thixotropic anaerobic thread locking compound ideal for bonding and sealing threads, and retaining of cylindrical parts. **TAFTLOCK 22** exhibits high resistance to heat, vibrations, water, gases, oils, hydrocarbons and many chemicals.

ADVANTAGES

- Ideal for thread locking small screws from loosening under vibration.
- Ideal for fasteners up to 6 mm diameters.
- Suitable for applications such as adjustment of set screws and small diameter fasteners where easy disassembly is required.

ADHESIVE PROPERTIES


Composition:	Dimethacrylate Ester
Color:	Purple
Viscosity: (Brookfield RVT, Spindle 3 @ 20 rpm)	1000 cps at 25°C
Specific Gravity:	1.05
Flash Point:	>100 °C
Shelf Life:	2 years

CURING PROPERTIES

Handling Cure Time:	20 minutes
Functional Cure Time:	1 – 3 hours
Full Cure Time:	24 hours
Breakaway Torque, ISO 10964: (M10 steel nuts and bolts N.m)	6 N.m (60 kgf/cm)
Prevail Torque, ISO 10964: (3/8 x 16 steel nuts and bolts)	4 N.m (40 kgf/cm)
Temperature Range:	-55 to 150°C

PHYSICAL PROPERTIES

Coefficient of Thermal Expansion (ASTM D696, K-1)	80×10 ⁻⁶
Coefficient of Thermal Conductivity (ASTM C 177, W/(m.k))	0.10
Specific Heat (kJ/kg.K)	0.30



All recommendations for the use of our products, whether given by us in writing, verbally, or to be implied from the results of tests carried out by us, are based on the current state of our knowledge. Notwithstanding any such recommendations the Buyer shall remain responsible for satisfying himself that the products as supplied by us are suitable for his intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility therefore. The Buyer shall ensure that the intended use of the products will not infringe any third party's intellectual property rights. We warrant that our products are free from defects in accordance with and subject to our general conditions of supply.

TECHNICAL DATA SHEET

TAFTLOCK 22

Anaerobic Thread Locker



CHEMICAL RESISTANCE


CHEMICAL	TEMPERATURE	% INITIAL STRENGTH RETAINED	
		500 hours	1'000 hours
Acetone	22°C	100	80
Ethanol	22°C	100	100
Motor Oil	125°C	100	100
Gasoline	22°C	100	100
Brake Fluid	22°C	100	100
Water / Glycol	87°C	90	85

APPLICATION METHOD

Surfaces should be dry, clean, and free of any contamination. Thread locker should be applied to the bolt in sufficient quantity to fill threads. **TAFTLOCK 22** performs the best in thin bond gaps. This thread locker is specifically formulated to give controlled friction and torque/tension ratio during assembly.

STORAGE

Anaerobic adhesives shall be ideally stored in a cool, dry place in unopened containers at room temperature between 8°C to 25°C. Please do not return any unused material to its original container.



All recommendations for the use of our products, whether given by us in writing, verbally, or to be implied from the results of tests carried out by us, are based on the current state of our knowledge. Notwithstanding any such recommendations the Buyer shall remain responsible for satisfying himself that the products as supplied by us are suitable for his intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility therefore. The Buyer shall ensure that the intended use of the products will not infringe any third party's intellectual property rights. We warrant that our products are free from defects in accordance with and subject to our general conditions of supply.